

Dencryl™ P11

Reactive, medium-viscosity primer for cement substrates

Description

Dencryl™ P11 resin is a medium-viscosity, transparent, solvent-free 2-component methacrylic resin that cures rapidly even at low temperatures if hardener is added. Its high viscosity makes **Dencryl™ P11** resin suitable for priming vertical and absorbent substrates with sufficient strength.

Application

Dencryl™ P11 resin is used as an adherent primer on concrete and cement substrates. The high viscosity means that a thick priming film is achieved.

Advice on application

Once the substrate has been inspected, it normally needs to be pre-treated. The necessary quantity of hardener must be adjusted in light of the temperature of the building. For the exact quantities, please refer to the table "Hardener dosages". You must not dose less than the given

quantity of hardening powder, as this will jeopardize the curing process. You must also avoid overdosing the hardening powder, as this can likewise lead to serious curing problems. If the pot life, within which good penetration of the substrate is guaranteed, is to be observed, appropriate batch quantities should be estimated. The material must be applied as soon as the hardening powder has finished dissolving in the resin components.

Dencryl™ P11 resin must be applied evenly without leaving puddles by means of a paint roller or brush. If rubber blades are used, the surface must always be rolled with a paint roller afterwards. Matt and heavily absorbent patches must be reprimed wet in wet before hardening until the pores are closed up. Resin consumption is about 0.4 kg/m².

Dencryl™ P11 0.7 – 1.2 mm can be sprinkled loosely into the fresh primer coat.

In the case of subsequent coating with **Dencryl™ B21** or **Dencryl™ M41** resin, **Dencryl™ P11** 0.7 – 1.2 mm (0.2 – 0.5 kg/m²) must always be sprinkled in. **Dencryl™ P11** resin must be completely cured before any further coat is applied.

Guideline recipe and batch quantities

Item	Component	Guideline recipe (% by weight)	Comments	Batch for 10 litre bucket
1	Dencryl™ P11	100 %		10 kg 10 litres
	Total:	100 %	Average consumption: 400 g/m²	10 kg 10 litres
2	Dencryl™ Hardening powder	2 – 6 % related to item 1	See "Hardener dosages" table for quantities	200 – 600 g

Characteristics of Dencryl™ P11 as delivered

Property	Measuring method	Approx. value
Viscosity at +20°C	DIN 53 015	270 – 330 mPa·s
Flow time at +20°C, 4 mm cup	DIN 53 211	47 – 53 sec.
Density D ₄ ²⁰	DIN 51 757	0.98 g/cm ³
Flash point	DIN 51 755	+10°C
Pot life at +20°C (100 g, 3 % pbw. hardening powder)		approx. 12 min.
Application temperature		+5°C to +30°C

Characteristics of Dencryl™ P11 in the hardened state

Property	Measuring method	Approx. value
Density	DIN 53 479	1.16 g/cm ³
Ultimate elongation	DIN 53 455	7 %
Shore-D	DIN 53 505	70 – 80 units
Water absorption, 4 days	DIN 53 495	125 mg (50 · 50 · 4 mm)
Water vapour permeability	DIN 53 122	1.05 · 10 ⁻¹¹ g/cm · h · Pa

Hardener dosages

Temperature	Hardening powder % pbw. *	Pot life approx. min.	Hardening time approx. min.
+5°C	6.0	15	50
+10°C	5.0	15	40
+20°C	3.0	12	35
+30°C	2.0	12	30

* The quantity of hardening powder is always related to the quantity of resin.

CE	
DenCoat · Calle Paraguay 14/2 · 35204 Vigo · Pontevedra · Spain	
10 ¹⁾	
P11 - 001	
EN 13813 SR-AR1-B1,5-IR4	
Synthetic resins for internal uses (Application in accordance with the newest technical information)	
Reaction to fire:	E II
Release of corrosive substances (Synthetic Resin Screed):	SR
Water permeability:	NPD ²⁾
Wear resistance (Abrasion Resistance):	AR 1 ³⁾
Bond strength:	B 1,5
Impact resistance:	IR 4
Sound insulation:	NPD ²⁾
Sound absorption:	NPD ²⁾
Thermal resistance:	NPD ²⁾
Chemical resistance:	NPD ²⁾

CE-labelling

- 1) Last two digits of the year in which the ce marking was affixed.
- 2) NPD = No performance determined.
- 3) Refers to a smooth surface without broadcasting.

DenCoat™ Tlf.: +45 88 44 22 27 · E-mail: info@dencoat.com · Website: www.dencoat.com

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to the technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out by only qualified experts in the sole responsibility of a customer. Please contact DenCoat for the latest version. All our documents, offers, ect. are in association with our general sales, delivery and application conditions.