

Denpox™ DPM

Damp Proofing Membrane

DESCRIPTION

Denpox™ DPM is a solvent free, low viscosity two component epoxy damp proofing membrane.

FEATURES AND BENEFITS

- Accepts up to 100% relative humidity
- Low viscosity
- Easy to apply
- Colored
- Excellent bond to substrate

FIELDS OF APPLICATION

Denpox™ DPM is used as a moisture barrier in concrete and accepts up to 100% relative humidity.

SUBSTRATE PREPARATION

All substrates must be structurally sound, clean and free from oil, grease and loose material and any other contamination which might impair adhesion. Mechanical preparation such as captive shot blasting, scarification, and diamond grinding for edge work should be used to produce a substrate surface profile suitable for the application of a resin finish. The tensile strength of the substrate should exceed 1.5MPa.

Denpox™ DPM should be applied when substrate temperatures are constant or falling to minimise the risk bubble and void formation due to expansion of air within the substrate when temperatures are rising. This is

particularly important to note on external applications. The curing reactions are influenced by the ambient, material and substrate temperatures. Low temperatures lengthen the pot life, open- and curing times. High temperatures shorten pot life, open- and curing times. The temperatures should not fall below the minimum stated until the material is fully cured. The temperature of the substrate must be at least 3°C above the dew point both during the application and for at least a further 24 hours (at 15°C).

APPLICATION

Denpox™ DPM (part A) is supplied in prepacked units along with **Denpox™ Hardener (part B)**. Before mixing, **Denpox™ DPM** should be homogenized by gentle stirring. precondition both A and B components to a temperature of approximately 15 to 20°C. Pour the entire contents of part B into the container of part A. Mix with a low speed (ca.300 rpm) electric drill and paddle for at least 3 minutes until homogeneous. Scrape the sides and the bottom of the container several times during mixing to ensure complete mixing. Keep the mixing head submerged to avoid entrapping air. Do not work out of the original container. Decant the mixed material into a fresh container and remix for another minute. **Denpox™ DPM** is applied by roller.

CONSUMPTION

Denpox™ DPM: Typically 0,3 kg/m² per layer.

CLEANING AGENT

Tools must be cleaned immediately after use with **Dencoat™ Tool Cleaner** or other suitable solvent.

PACKAGING

Denpox™ DPM is supplied in 16 kg buckets. **Denpox™ DPM** is used with 5 kg **Denpox™ Hardener**.

SHELF LIFE

Minimum 12 months stored in original containers under dry conditions at a temperature between 15-20°C. Do not expose to direct sunlight.

Technical data for Liquid material

Property	Method	Values
Mixing Ratio A:B		12.5 kg : 3.75 kg
Mixed density		1.3 kg/l
Mixed Viscosity at 23°C	Brookfield DV-II	350 cP
Working time at 23°C		30 minutes
Ready for traffic at 23°C		12 hours
Fully cured 23°C		7 days
Substrate temperature		Min 5°C max 30°C
Max relative humidity		Max 85%

Technical data cured material

Property	Method	Values
Thickness		0.3 mm
SHORE D hardness	DIN 53505	80
Tensile strength	DIN 53504	n.a.
Elongation at Break	DIN 53504	>50%
Crack bridging ability		1 mm
Temperature resistance		Max 90°C
Water penetration		Impervious
Chemical Resistance		See separate datasheet
Adhesion to concrete	BS/EN 24614	>1.5 MPa
Abrasion resistance (Taber)	EN 1504-2	<3000 mg
Impact resistance	EN 1504-2	Class II
Fire classification	EN 1504-2	D _{fl}



DenCoat™ International · E-mail: info@dencoat.com · Website: www.dencoat.com

22¹⁾

DPM - 001

EN 13813 SR-AR1-B1,5-IR4

Synthetic resins for internal uses
(Application in accordance with the newest technical information)

Reaction to fire:	D _{fl}
Release of corrosive substances (Synthetic Resin Screed):	SR
Water permeability:	NPD ²⁾
Wear resistance (Abrasion Resistance):	< AR 1 ³⁾
Bond strength:	> B 1,5
Impact resistance:	< IR 4
Sound insulation:	NPD ²⁾
Sound absorption:	NPD ²⁾
Thermal resistance:	NPD ²⁾
Chemical resistance:	NPD ²⁾

CE-labelling

- 1) Last two digits of the year in which the ce marking was affixed.
- 2) NPD = No performance determined.
- 3) Refers to a smooth surface without broadcasting.

DenCoat™ E-mail: info@dencoat.com · Website: www.dencoat.com

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to the technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out by only qualified experts in the sole responsibility of a customer. Please contact DenCoat for the latest version. All our documents, offers, ect. are in association with our general sales, delivery and application conditions.

w w w . d e n c o a t . c o m