

# Denpur™ Hardener

Polymeric MDI

## DESCRIPTION

Polymeric MDI

## FIELDS OF APPLICATION

Hardener for Denpur™ products.

## CONSUMPTION

Consult specific Denpur™ datasheet.

## PACKAGING

Denpur™ Hardener is supplied in 1; 2.5; 3.5 and 5 kg and 1150 kg units.

## SHELF LIFE

Minimum 12 months stored in original containers under dry conditions at a temperature between 15-20°C. Do not expose to direct sunlight.

## Technical data for Liquid material

Property	Method	Values
NOC%		31.5-32.5
Density		1.23 g/ml
Viscosity		60 cP
Solid content		100%
Gardner colour		n.a.

**DenCoat™** E-mail: [info@dencoat.com](mailto:info@dencoat.com) · Website: [www.dencoat.com](http://www.dencoat.com)

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to the technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out by only qualified experts in the sole responsibility of a customer. Please contact DenCoat for the latest version. All our documents, offers, ect. are in association with our general sales, delivery and application conditions.