

Denspartic™ CC

Polyaspartic Clear Coat

DESCRIPTION

Denspartic™ CC is a two component, clear aliphatic polyaspartic coating. It provides excellent abrasion resistance, improved scratch resistance and a clear finish.

FEATURES AND BENEFITS

- Consistent, slightly textured clear finish
- Durable
- Improves scratch resistance and abrasion resistance
- UV-resistant
- Good adhesion to non-porous substrates
- Low viscosity
- Easy to clean and maintain

FIELDS OF APPLICATION

Denspartic™ CC is designed for use as a clear UV stable durable topcoat for polyurethane and epoxy coating systems.

SUBSTRATE

The surface to be applied **Denspartic™ CC** must be clean and dry. Application should be made within 24 hours after installation of the sub layer.

APPLICATION

Denspartic™ CC is supplied in prepacked units. Before mixing, **Denspartic™ CC** should be homogenized by gentle stirring. Precondition both A and B components to a temperature of approximately 15 to 20°C.

Pour the entire contents of part B into the container of part A. Mix with a low speed (ca. 300 rpm) electric drill and paddle for at least 3 minutes until homogeneous. Scrape the sides and the bottom of the container several times during mixing to ensure complete mixing. Keep the mixing head submerged to avoid entrapping air. Do not work out of the original container. Decant the mixed material into a fresh container and remix for another minute.

Always work wet-in-wet otherwise you risk getting visible roller marks. Use a max. 40 cm wide short haired roller and start in the middle of one of the short sides of the floor. Dip the roller in the mixed material and apply a strip of **Denspartic™ CC** parallel to the wall next to one of the corners. Dip the roller in the material again and apply as a path from the starting point and out of the other corner. Go back and repeat these steps while overlapping the first track with a few centimetres.

With a new roller scroll backwards without stopping from one corner to the next. Offset roller with 10 to 20 cm and roll to the opposite wall without stopping. Always roll in same direction to avoid visual differences.

By using this method, the period between overlaps should not exceed 1-4 minutes, and visible roller marks will be minimized. Depending on the application method and the consumption, **Denspartic™ CC** appears with a slightly structured surface. This has no influence on the final properties of the coating.

The curing time of the material is influenced by the ambient, material and substrate temperatures. At low temperatures, the chemical reactions

are slowed down; this lengthens the pot life, open time and curing times. High temperatures speed up the chemical reactions thus the time frames mentioned above are shortened accordingly. To fully cure, the material, substrate and application temperature should not fall below the minimum. The temperature of the substrate must be at least 3°C above the dew point both during the application and for at least 8 hours after application (at 15°C).

CONSUMPTION

Denspartic™ CC: Typically 0.05- 0.15 kg/m² per layer.

Do not exceed the recommended use.

CLEANING AGENT

Tools must be cleaned immediately after use with **Dencoat™ Tool Cleaner** or other suitable solvent.

PACKAGING

Denspartic™ CC is supplied in 6.5 kg. **Denspartic™ CC** is used with **Denspartic™ Hardener** in appropriate quantity.

SHELFLIFE

Minimum 12 months stored in original containers under dry conditions at a temperature between 15-20°C. Do not expose to direct sunlight.

Technical data for Liquid material

Property	Method	Values
Mixing Ratio A:B		6.5 kg : 2 kg
Mixed density		1.07 kg/l
Mixed Viscosity at 23°C	Brookfield DV-II	100 cP
Working time at 23°C		20 minutes
Ready for traffic at 23°C		1 hour
Fully cured 23°C		24 hours
Substrate temperature		Min 5°C max 30°C
Max relative humidity		Max 85%

Technical data cured material

Property	Method	Values
Thickness		0.05 - 0.1 mm
SHORE D hardness	DIN 53505	n.a.
Tensile strength	DIN 53504	
Elongation at Break	DIN 53504	>50%
Crack bridging ability		1 mm
Temperature resistance		Max 90°C
Water penetration		Impervious
Chemical Resistance		See separate datasheet
Adhesion to concrete	BS/EN 24614	>1.5 MPa
Abrasion resistance (Taber)	EN 1504-2	<50 mg
Impact resistance	EN 1504-2	Class II
Fire classification	EN 1504-2	n.a.



E-mail: info@dencoat.com · Website: www.dencoat.com

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to the technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out by only qualified experts in the sole responsibility of a customer. Please contact DenCoat for the latest version. All our documents, offers, ect. are in association with our general sales, delivery and application conditions.